



# *Leslie Ceramic Supply*

## Mixing Formulae for Dry Glaze

<b>For:</b>	<b>Mix with:</b>		
<b>Dipping</b>	Water	10.5 to 11.5 oz.	<b>per pound dry glaze</b>
	Bentonite	0 to 2.3 g.	
<b>Spraying</b>	Water	7.5 to 8.5 oz.	<b>per pound dry glaze</b>
	Bentonite	1.1 to 3.4 g.	
<b>Brushing</b>	Water	6.5 to 7.5 oz.	<b>per pound dry glaze</b>
	Bentonite	4.5 to 6.8 g.	
	CMC Powder	2.3 to 4.3 g.	

copyright 2010 leslie ceramic supply co., inc.